



## Technical data sheet: GO

Solid graphene oxide.

### Description:

Solid graphene oxide (GO) produced by chemical graphite exfoliation. The product can be easily redispersed on water or solvents.



### Main features:


Chemical analyses, values expressed on mass percentage:

Carbon, C	42%
Oxygen, O	47%
Hydrogen, H	2,4%
Sulfur, S	<2%

---

**AMBROGI S.A.S.**

Via Goldoni, 4 – 40033 Casalecchio di Reno (BO), Italy  
Phone: +39 347 1576397; Fax: +39 051 0821685;  
email: [service@ambrogiconsulting.com](mailto:service@ambrogiconsulting.com)



## Technical data sheet: GO

This data sheet briefly describes and gives typical data for some of the basic properties of GO. It is emphasized that all data in this publication have been obtained from laboratory tests on representative samples. Thus, although the values are typical, they are for very general guidance and must not be used as a basis for specifications.

Values on specific production lot are available upon request.

Sample should be stored dry and away from direct sources of heat. More detailed information and advice on individual products may be obtained from the Sales Contacts.

Information contained in this publication, and otherwise supplied to users, are based on our general experience and are given in good faith, but we are unable to accept responsibility in respect of factors which are outside our knowledge or control.

**Is the responsibility of the customer to ensure that the use complies with all relevant regulation.**

---

**AMBROGI S.A.S.**

Via Goldoni, 4 – 40033 Casalecchio di Reno (BO), Italy  
Phone: +39 347 1576397; Fax: +39 051 0821685;  
email: [service@ambrogiconsulting.com](mailto:service@ambrogiconsulting.com)